



# |ME Ultra Grind® II

## ME Ultra Grind® II:

- 2.0" to 4.0" (65-100 mm)
- Designed for maximum productivity and low operating costs in ball milling

### Chemistry

Limits	C	Mn	P (max.)	S (max.)	Si	Cr	Mo
Upper Limit	1.20	1.10	0.025	0.025	0.40	2.00	0.05
Lower Limit	1.00	0.95	-	-	0.20	1.50	-

### Hardness (HRC)

Series	Surface (min. - max.)		Volumetric (min. - max.)		Applications
ME Ultra Grind II	50	60	54	60	Ball mills